



DATA SHEET

Filter media

Blended 90/10 Flame Retardant

Blended 90/10 Flame Retardant

Appearance	White, corrugated
Use	Pleatable filter media
Composition	Blended Cellulose + Synthetic
Area weight	135 g/m ²
Thickness	0.35 mm
Air Permeability (Tappi T251)	190 l/m ² s
Temperature (dry heat)	
Continuous	65 °C
Peaks	80 °C
Chemical resistance	
Hydrolysis	N/A
Acids	Poor
Alkalis	Fair
Oxidising agents	Poor
Organic solvents	Fair
Abrasion resistance	Good
Supports combustion	No. Flame retardant class F1/K1
Application field	Fine dust fumes caused by laser and plasma cutting, welding fumes, shot blasting.

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM0837101 • Rev. 00 • 0120

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.