



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter media

Polyester Anti-Static

Polyester Anti-Static

Appearance	Grey
Use	Pleatable filter media
Composition	100% Polyester Spunbonded
Area weight (g/m²)	270
Thickness (mm)	0.63
Air Permeability (m³/m²/h - 200 PA)	670
Surface electrical resistance (Ohm)	$\rho < 10^3 \Omega$
IFA/BIA certificate (DIN EN 60335-2-69:2008)	M
Max. working temperature (C°)	150
Volume of pores (%)	68
Application field	Paper, powder painting, aluminium, toner, sugar, pigments, pvc, zinc, titanium, graphite, meal, tobacco, arc plasma, ceramic painting powder, plastic material processing, resin, epoxy material, metal coating.

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM06591A • Rev. 10 • 0319

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.