



DATA SHEET

Filter media
Polyester Anti-Static

Polyester Anti-Static

Treatment	Conductive / Anti-Static
Use	Pleatable filter media
Composition	100% Polyester
Area weight	250 g/m ²
Thickness	0.56 mm
Air Permeability	510 m ³ /m ² /h at 200 Pa
Measured according DIN EN 1149-1	5 x 10 ³ on the metallic coated side of the media
IFA/BIA certificate (DIN EN 60335-2-69:2015)	M
Temperature (dry heat)	
Continuous	120 °C
Peaks	140 °C
Chemical resistance	
Oil/Water	Good
Hydrolysis	Good
Acid	Good
Alkali	Fair
Dust release	Excellent

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM06598N • Rev. 03 • 0322

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.