



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter media Standard Polyester

Standard Polyester

Appearance	White, uncorrugated
Use	Pleatable filter media
Composition	Spunbond polyester
Area weight	250 g/m ²
Thickness	0.57 mm
Air Permeability (DIN 29073)	470 m ³ /m ² .h at 200 Pa
ISO Classification ISO 16890-2:2016(E) CERTIFICATE	ePM ₁₀ 65% Test report number: 170-2
Temperature (dry heat)	
Continuous	93 °C
Peaks	110 °C
Chemical resistance	
Hydrolysis	N/A
Acids	Good
Alkalis	Good
Oxidising agents	Good
Organic solvents	Good
Abrasion resistance	Excellent
Supports combustion	Yes
Application field	Wide pleat spacing provides excellent particle release. Highly recommended for chemical, food, and industrial processing when product contamination must be minimised. Excellent performance on moist, hygroscopic or agglomerative dust.

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM0506401 • Rev. 12 • 0820

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.