



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter media

Polyester Anti-Static

Polyester Anti-Static

Appearance	Grey, corrugated
Use	Pleatable filter media
Composition	Spunbond polyester with aluminised coating
Area weight	260 g/m ²
Thickness	0.61 mm
Air Permeability (Frazier)	360 m ³ /m ² .h at 125 Pa
Surface finish	Aluminised
Surface electrical resistance (DIN 54345)	Less than 10 ⁸ Ω (on the Anti-Static coated side)
IFA/BIA certificate (DIN 660335-2-69)	N/A
Temperature (dry heat)	
Continuous	93 °C
Peaks	110 °C
Chemical resistance	
Hydrolysis	N/A
Acids	Good
Alkalis	Good
Oxidising agents	Good
Organic solvents	Good
Abrasion resistance	Excellent
Supports combustion	Yes
Application field	Wide pleat spacing provides excellent particle release. Highly recommended for chemical, food and industrial processing, when product contamination must be minimised. Excellent performance on moist, hygroscopic or agglomerative dust. Chemical processing, food processing, general industrial.

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM1215801 • Rev. 00 • 1019

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.